



Testing Centre ALMI TEST
 Acad. G. Bonchev, bl. 24
 1113 Sofia, Bulgaria
 e-mail: office@almitest.com
 tel.: +359 888 334 717
 tel.: +359 2 97 97 119
 fax: +359 2 97 97 119
www.almitest.com

Certificate for accreditation
 No 2 LIK/31.05.2016, valid
 31.05.2020, issued by EA BAS
 acc. BDS EN ISO/ IEC
 17025:2006

TEST REPORT № 5262459010688 23.08.2016

Sample

Sample description	Knitted fabric 100 % PE with metal thread, colour light grey
Client's order number	-
Sampling	Sample delivered by the client
Laboratory sample code	5262

Test methods

Reference Number	BDS EN 12127: 2000; BDS EN ISO 3175-2: 2010; BDS EN ISO 5077: 2008; BDS EN ISO 6330: 2012; DIN 53894-2: 1979 -02; Ordinance for names of textile products (SG 44/ 2006); СД CEN ISO/TS 16179: 2013;
------------------	---

Client

Name	Rivov Electronics Ltd.		
Address	Bulgaria , Haskovo , zh.k. Orfey, bl. 1, vh. B, ap. 31		
Order number	5262	Order date	09.08.2016
Date of receiving samples	09.08.2016	Date of test	18.08.2016

Director:
 (name, signature, stamp)



This test report is issued by Testing Centre ALMI TEST under its General Conditions of Service available at www.almitest.com. All results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of Testing Centre ALMI TEST. Copies of the test report are valid only with original wet and dry stamps of Testing Centre ALMI TEST.

TESTING CENTRE ALMI TEST TEST REPORT № 5262459010688 23.08.2016

Test results

Sample description Knitted fabric 100 % PE with metal thread, colour light grey
 Laboratory sample code 5262

№	Test	Measurement unit	Test method	Test result	Limit value	Test conditions
1	Fiber composition	%	Ordinance for names of textile products (SG 44/2006)	Polyester 61,6 Metal thread 38,4	-	Manual
2	Mass per unit area	g/m ²	BDS EN 12127:2000	141	-	20°C, 65% RH
3	Dimensional changes at ironing	%	DIN 53894-2: 1979 -02	Wales -11,5 Courses -0,1	-	Ironing press
4	Dimensional change at washing	%	BDS EN ISO 5077:2008; BDS EN ISO 6330: 2012	Wales +1,1 Courses -10,8	-	Washing at 30 °C (BDS EN ISO 6330: 2012, procedure 3N), drying method C
5	Dimensional changes at dry cleaning	%	BDS EN ISO 3175-2: 2010	Wales -6,0 Courses -15,3	-	-
6	Content of organotin compounds	mg/kg	СД CEN ISO/TS 16179: 2013	BuT (CAS 1118-46-3) <0,2 MOT (CAS 3091-25-6) <0,2 DBT (CAS 683-18-1) <0,2 DOT (CAS 3542-36-7) <0,2 TBT (CAS 1461-22-9) <0,2 TPhT (CAS 639-58-7) <0,2 TCyT (CAS 3091-32-5) <0,2 TeBT (CAS 1461-25-2) <0,2	-	Derivatization, organic solvent extraction

Specialist:

Vinova, Duff
 (name, signature)

Director:

Stoycheva M
 (name, signature, stamp)



This test report is issued by Testing Centre ALMI TEST under its General Conditions of Service available at www.almitest.com. All results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of Testing Centre ALMI TEST. Copies of the test report are valid only with original wet and dry stamps of Testing Centre ALMI TEST.